

**AMENDMENTS TO THE ABSTRACT**

Please replace the paragraph beginning at page 47, line 2, with the following rewritten paragraph:

-- ~~Disclosed is a~~ A coating liquid for forming a transparent conductive film, comprising conductive fine particles having an average particle diameter of 1 to 200 nm, silica particles having an average particle diameter of 4 to 200 nm and a polar solvent. The silica particles are in the form of chain silica particles having 2 to 10 silica particles on an average being connected. The content of an alkali in the silica particles is not more than 1000 ppm in terms of an alkali metal M. ~~Also disclosed is a~~ A substrate with a transparent conductive film, comprising a substrate, a transparent conductive fine particle layer formed on the substrate and containing conductive fine particles having an average particle diameter of 1 to 200 nm and silica particles having an average particle diameter of 4 to 200 nm and/or chain silica particles having 2 to 10 silica particles on an average being connected, and a transparent film provided on the transparent conductive fine particle layer and having a refractive index lower than that of the transparent conductive fine particle layer. A display device using the substrate with a transparent conductive film is further disclosed. ~~The coating liquid for forming a transparent conductive film is capable of forming a transparent conductive film having low surface resistance, excellent antistatic properties, excellent electromagnetic blocking properties, high film strength and excellent adhesion to a substrate.~~